

IN THE CLAIMS

Please amend claims 36 and 37, as follows:

1. (Withdrawn) An article of apparel comprising an insulating component incorporated into the article of apparel, wherein the improvement comprises an insulating component comprising an insulating structure comprising a) a gas impermeable envelope and b) a porous material contained within the envelope, wherein the insulating structure has a thermal conductivity of less than or equal to 25mW/m K at 25°C.
2. (Withdrawn) The article of apparel of claim 1, wherein apparel comprises headwear, footwear or handwear.
3. (Withdrawn) The article of apparel of claim 1, wherein apparel comprises a boot.
4. (Withdrawn) The article of apparel of claim 1, wherein the insulating structure has a thickness of 10 mm or less.
5. (Withdrawn) The article of apparel of claim 1, wherein the insulating structure has a thickness of 3 mm or less.
6. (Withdrawn) The article of apparel of claim 1, wherein the insulating structure has a thermal conductivity less than 20 mW/m K.
7. (Withdrawn) The article of apparel of claim 1, wherein the insulating structure has a thermal conductivity between about 15-18 mW/m K.
8. (Withdrawn) The article of apparel of claim 1, wherein the envelope is at least partially evacuated.
9. (Withdrawn) The article of apparel of claim 1, wherein the porous material has a pore size of 100 nm or less.

10. (Withdrawn) The article of apparel of claim 1, wherein the porous material has a pore size of 20nm or less.
11. (Withdrawn) The article of apparel of claim 1, wherein the porous material is selected from metal oxides.
12. (Withdrawn) The article of apparel of claim 1, wherein the porous material is fumed silica.
13. (Withdrawn) The article of apparel of claim 1, wherein the porous material is an aerogel.
14. (Withdrawn) The article of apparel of claim 13, wherein the aerogel comprises silica.
15. (Withdrawn) The article of apparel of claim 1, wherein the insulating structure further comprises a binder.
16. (Withdrawn) The article of apparel of claim 1, wherein the insulating structure further comprises carbon or titanium dioxide.
17. (Withdrawn) The article of apparel of claim 1, wherein the envelope comprises a gas having a molecular weight greater than that of air.
18. (Withdrawn) A method of forming an insulated apparel article comprising providing an insulating component; and incorporating an insulating component into the article of apparel, wherein the insulating component comprises an insulating structure comprising a) a gas impermeable envelope and b) a porous material contained within the envelope, wherein the insulating structure has a thermal conductivity of less than or equal to 25 mW/m K at about 25°C.
19. (Withdrawn) The method of claim 18, wherein the insulated apparel article has inner and outer textile layers and the method further comprised incorporating the insulating component between the inner and outer layers.

20. (Withdrawn) The method of claim 18, wherein the insulated apparel article has inner and outer textile layers and the method further comprises affixing the insulating component to the inner textile layer.
21. (Withdrawn) The method of claim 18, wherein the insulated apparel article has inner and outer textile layers and the method further comprises affixing the insulating component to the outer textile layer.
22. (Withdrawn) A method of increasing the thermal insulation value of an article of apparel without substantially changing the fit of the article comprising providing an article of apparel, providing a insulating component comprising a gas permeable envelope and a porous material contained within the envelope, wherein the insulating structure has a thickness of about 3mm or less and comprises a thermal conductivity of less than or equal to 25 mW/m K at 25°C, and incorporating the insulating component into the article of apparel.
23. (Withdrawn) The method of claim 22, wherein the article of apparel has a thermal insulation value of about 0.3 to 1.7 m²K/W.
24. (Withdrawn) The method of claim 22, wherein the insulating structure has a thickness of about 2mm or less.
25. (Withdrawn) A method of insulating a person from environmental conditions comprising providing an insulated article of apparel, and positioning the insulated article of apparel between the environment and the person, wherein the insulated article of apparel comprises an insulating component comprising an insulating structure having a) a gas impermeable material and b) a porous material contained within the envelope, the insulating structure having a thermal conductivity of less than or equal to 25 mW/m K at 25°C.
26. (Withdrawn) The method of claim 25, wherein the environment is a low temperature environment.

27. (Previously presented) A method of insulating a boot comprising
 providing a boot having a toe cap area, a boot upper and a boot sole;
 providing a mixture comprising a porous material selected from fumed
 metal oxide and aerogel;
 compressing the mixture to form a structure material,
 placing the structure material in a gas impermeable envelope,
 evacuating air from the envelope at reduced pressure, and sealing the
 envelope, to form a flat insulating structure;
 shaping the flat insulating structure from a flat structure into a shaped
 insulating structure that is shaped to cover a front top portion of a foot of a
 wearer; and
 inserting the shaped insulating structure into the toe cap area of the
 boot, the shaped insulating structure having a thermal conductivity of less
 than or equal to 25 mW/m K at 25°C.
28. (Previously presented) The method of claim 27, wherein the boot comprises
 inner and outer boot layers and the shaped insulating structure is positioned
 between the layers.
29. (Previously presented) The method of claim 27, wherein the shaped
 insulating structure is affixed to an inner boot layer and adjacent a wearer of
 the boot.
30. (Previously presented) A method of insulating a boot comprising
 providing a boot having a toe cap area, a boot upper and a boot sole;
 providing a mixture comprising a porous material selected from fumed
 metal oxide and aerogel;
 compressing the mixture to form a structure material,
 placing more than one section of the structure material in a gas
 impermeable envelope,
 evacuating and sealing the envelope at reduced pressure, to form a flat
 insulating structure comprising more than one section of structure material
 within the envelope;
 sealing the envelope between sections of the structure material within
 the envelope to provide flexibility to the flat insulating structure for shaping;

shaping the flat insulating structure from a flat insulating structure into a form of a shaped insulating structure; and

inserting the shaped insulating structure into the toe cap area of the boot, the shaped insulating structure having a thermal conductivity of less than or equal to 25 mW/m K at 25°C.

31. (Previously presented) The method of claim 30, wherein the flat insulating structure has a loss of thickness of 20% or less at a pressure of 1 atmosphere.
32. (Previously presented) The method of claim 30, wherein the flat insulating structure has a loss of thickness of 10% or less at a pressure of 1 atmosphere.
33. (Previously presented) The method of claim 30, wherein the porous material is a fumed metal oxide.
34. (Previously presented) The method of claim 30, wherein the porous material is fumed silica.
35. (Previously presented) The method of claim 30, wherein the porous material is fumed alumina.
36. (Currently amended) The method of claim 27, wherein the flat insulating structure is shaped into ~~[[a]]~~ the form of a curved shaped insulating structure ~~in the form of a~~ that corresponds to the toe cap area of the boot.
37. (Currently amended) The method of claim 30, wherein the flat insulating structure is shaped into ~~[[a]]~~ the form of a curved shaped insulating structure ~~in the form of a~~ that corresponds to the toe cap area of the boot.
38. (Previously presented) The method of claim 27, wherein the gas impermeable envelope is under a vacuum pressure of up to about 10,000Pa.

39. (Previously presented) The method of claim 27, wherein the gas impermeable envelope is under a vacuum pressure of about 1,000Pa or less.
40. (Previously presented) The method of claim 30, wherein the gas impermeable envelope is under a vacuum pressure of up to about 10,000Pa.
41. (Previously presented) The method of claim 30, wherein the gas impermeable envelope is under a vacuum pressure of about 1,000Pa or less.
42. (Previously presented) The method of claim 30, wherein the boot comprises inner and outer boot layers, and the method further comprises positioning the insulating component between the inner and outer boot layers.
43. (Previously presented) The method of claim 30, wherein boot comprises an inner boot layer, and the method further comprises affixing the insulating component to the inner boot layer adjacent a wearer of the boot.
44. (Previously presented) The method of claim 27, wherein the method comprises forming a flat insulating structure having a thickness of less than 3mm.
45. (Previously presented) The method of claim 27, wherein the method comprises forming a flat insulating structure having a thickness of 2mm or less.
46. (Previously presented) The method of claim 30, wherein the method comprises forming a flat insulating structure having a thickness of less than 3mm.
47. (Previously presented) The method of claim 30, wherein the method comprises forming a flat insulating structure having a thickness of 2mm or less.
48. (Canceled)
49. (Canceled)